




# Wire Rope



17x7+FC



18x7+FC



18x7+IWRC

Used in lifting on Cableway

Nominal Diameter		Approximate Weight		Nominal Tensile Strength (N/mm <sup>2</sup> )					
				1670		1770		1870	
mm	Inch	kg/100m		Min. Breaking Strength (KN)					
		FC	IWRC	FC	IWRC	FC	IWRC	FC	IWRC
6	1/4	14	14.7	19.1	19.8	20.4	21	21.6	22.2
8	5/16	24.6	25.8	34.2	35.2	36	37.2	38.3	39.4
10	13/32	38.5	40.4	53.2	54.8	56.5	58.2	67.5	69.5
12	1/2	56.2	58.9	76.6	78.9	81.3	83.7	85.8	88.4
14	9/16	75.8	79.4	104.9	108	110.2	113.5	117	120.5
16	5/8	98.5	103.1	140.8	145	144.2	148.5	152.9	157.5
18	11/16	124	129.8	171.8	177	183.1	188.6	192.6	198.4
20	13/16	153	160.2	212.3	219.5	225.8	232.6	238.2	245.3
22	7/8	186.5	195.2	257.5	265.2	272.6	280.8	287.6	296.2
26	1	160	272.2	359.6	370.4	380.7	392.1	401.9	414
28	1-1/8	302	316.2	416.6	429.1	441.8	455.1	466.2	480.2
30	1-3/16	345	316.2	475.7	490	504.9	520	534	550
32	1-1/4	395	413.5	542.2	558.5	563.1	580	592.2	610

(Remark: All Weights & Dimensions are approximate, the measurements may vary between different factories)